

DULUX GLOSS ENAMEL

TECHNICAL DATA SHEET

Version 4 – 2019 SEPTEMBER

THIS ISSUE SUPERSEDES ALL PREVIOUS PUBLICATIONS

PRODUCT DESCRIPTION

High quality interior or exterior enamel for surfaces where a glossy durable finish is required

PRODUCT USES

- Suitable for use on all interior and exterior walls and trim (frames and doors), providing new or previously painted surfaces have been suitably prepared.

FEATURES AND BENEFITS

- Extremely durable.
- Colour fade resistant – protection against harsh UV rays.
- Scratch and stain resistant.
- Superb appearance with even gloss finish.

PRODUCT INFORMATION

Appearance	High Gloss
Colour	White, a range of ready-mixed colours, and colours from the Dulux Colour System.
Binder Type	Alkyd
Density at 23°C	Approx. 1.10
Solids Content	By weight: Approx. 47% By volume: Approx. 34%
Packaged Viscosity	Viscosity at 23°C: Approx. 80KU
Spreading Rate	Approx. 8m ² -10m ² per litre depending on surface porosity, profile and application method.
Recommended DFT per coat	Min. 25µm. Max. 35µm.
Recommended WFT per coat	Min. 75µm. Max. 100µm
Flash Point	37°C

DULUX GLOSS ENAMEL

APPLICATION INFORMATION

Mixing	Stir until homogeneous with a flat paddle.
Application Surface conditions	Surface Temperature between 10 - 35°C. Relative Humidity between 10 - 85 % OR 2°C above dew point minimum.
Application methods	Brush, Roller (short-nap mohair or foam), or airless spray.
Thinner	Thinning not recommended. Ready for use after thorough stirring.
Drying Time	Surface dry 4 hours at 23°C.
Recoating Time	18 hours at 23°C (Drying times will be extended during cold, wet or humid conditions.)
Cleaning of equipment	After use, remove as much product as possible, and then clean immediately with Dulux Brush Cleaner Degreaser or Mineral Turpentine.
Substrates	Suitable for cement plaster, gypsum plaster, concrete, fibre cement, PVC, galvanised iron (non-roof sheeting), ferrous metal and wooden surfaces provided that appropriate preparation and priming is carried out.
Precautions:	Do not apply during cold (below 10°C) or wet weather. Do not apply directly to substrate without priming. Not suitable for direct application to powdery or friable surfaces whether previously painted or not.
Coats Required	Apply two to three finishing coats to new surfaces to achieve a continuous closed film and solid colour.

SURFACE PREPARATION

Ensure that surfaces are sound and free from dust, oil, grease, dirt, and debris. Surfaces must be thoroughly dry - no more than 12% moisture content.

NEW SURFACES

Cement Plaster (non-friable), Composite Boarding and Fibre Cement

- It is recommended that fresh plaster should be allowed one week drying for every 5mm thickness; and longer in cold or damp weather.
- Spot-prime metal strips and nail heads with appropriate metal primer.
- Prime with one coat of **Dulux Plaster Primer** or **Dulux Trade Plaster Primer**, followed by one coat of **Dulux Universal Undercoat** or **Dulux Trade Universal Undercoat**.

DULUX GLOSS ENAMEL

SURFACE PREPARATION

Gypsum Plaster (non-friable)

- Ensure the gypsum plaster is sound and non-friable and cured as per the manufactured of the gypsum plaster specifications.
- Apply one coat **Dulux Plaster Primer** or **Dulux Trade Alkali Resistant Primer**. Very absorbent gypsum plaster could require more primer coats to achieve correct binding and sealing properties.

Concrete

- Remove any uncured cement, grease, and mould release agents by high-pressure water blast, or wash with a strong solution of **Dulux Pre-Paint Sugar Soap** /water solution. Rinse off thoroughly with clean water and allow drying out.
- For best paint system performance prime with one full coat **Dulux Plaster Primer** or **Trade Alkali Resistant Primer**.

Galvanised Iron, Aluminium and all non-ferrous metals (non-roof sheeting)

- For unpainted but weathered galvanised iron - Remove all loose rust and scale by means of wire brushing, sanding, chipping, or mechanical scouring - down to bright metal.
- Remove all traces of temporary protective coating, dirt, grease, salts and zinc corrosion (white rust) from the surface with **Dulux Galvanised Iron Cleaner**. Ensure complete removal of **Dulux Galvanised Iron Cleaner** by rinsing with running water. A water-break free surface indicates thorough cleaning - running water should not form droplets. If a water-break free surface was not achieved, repeat the cleaning process. Prime immediately after cleaning.
- Prime with one to two coats **Dulux Galvanised Iron Primer** depending on the severity of the conditions. Two coats recommended for coastal conditions and chemical works.
- For best paint system performance follow primer with **Dulux Universal Undercoat** before applying the selected finishing coat.

Mild Steel and Iron

- Inspect shop-primer thoroughly for damage by installation. All rust, scale and dirt must be removed by scraping or with steel wire brushes, and then thoroughly sand with medium grit sandpaper and finish with fine grit sandpaper - down to a bright metal finish. Ensure that the sanded areas are dry and free of grease and dust. A solvent wash (rags dipped in lacquer thinner) may be used. Change the rags frequently. Allow drying.
- Prime with one to two coats **Dulux Steel Primer**, depending on the severity of the conditions. Two coats recommended for coastal conditions.
- For best paint system performance follow primer with **Dulux Universal Undercoat** before applying the selected finishing coat.

DULUX GLOSS ENAMEL

SURFACE PREPARATION

Rigid PVC Surfaces

- Lightly sand surfaces to improve adhesion. Clean and degrease with **Dulux Sugar Soap**/water solution. Rinse thoroughly with water and allow drying.
- Prime with one coat **Dulux Supergrip**

Wooden Surfaces

- Timber treated with borer- or fire retardant may cause slow drying (consult supplier).
- Treat knots in timber with Knotting Agent.
- Spot prime nail heads with **Dulux Steel Primer**.
- Special attention must be given to painting the end grain to avoid moisture penetration - apply a second coat after 10 - 20 minutes.
- Prime with one coat **Dulux Wood Primer**. Two coats may be required for very absorbent wood.
- For best paint system performance follow **Dulux Wood Primer** with **Dulux Universal Undercoat** before applying the selected finishing coat.

PREVIOUSLY PAINTED SURFACES

Good Condition, not powdery

- Remove all rust scale back by most suitable means back to bright clean metal or galvanised surface. Any loose and flaking paint must be removed back to a sound substrate and firm edges by scraping and sanding.
- Treat as for new surfaces.

Old Paint in Poor Condition

- Completely remove all loose and flaking paint.
- Remove oil, grease dirt or any other contaminants with **Dulux Sugar Soap**/water solution and allow drying.
- Friable surfaces must be removed and repaired.
- Chalked surfaces must be thoroughly brushed or prepared with high pressure water cleaning. NOTE: While this product can be used for sealing exterior chalked or slightly friable surfaces, it will not penetrate thick layers of powdery material. **Dulux Bonding Liquid**, which is un-pigmented, is preferred.
- Mould instructions. To kill lichen and algae growth, scrub with one of the following solutions: either 4:1 water/chlorine, or 4:1 water/sodium hypochlorite. Ensure that the areas are completely saturated, and allow the solution to react for a minimum of 4 hours. Rinse the complete wall surface thoroughly with clean water and allow drying.
- Prime all exposed areas with appropriate primer as for new surfaces

DULUX GLOSS ENAMEL

FILLING

Fill all imperfections with the appropriate **Dulux Pre-Paint filler** and spot prime filled areas with **Dulux Plaster Primer** once the crack filler has dried properly. Failure to do this will result in uneven sheen levels between the repaired and normal areas.

HEALTH AND SAFETY INFORMATION

This product contains no added lead. Avoid contact with skin or eyes. Keep out of reach of children. If accidentally swallowed, seek medical advice immediately and show this container to the doctor. Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding should be used wherever possible.

If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used. Do not empty into drains or watercourses. Ensure good ventilation during application and drying. It is recommended to use suitable protective clothing and equipment. To avoid the risk of spillage, always store and transport containers in a secure upright position. Refer to Material Safety Data Sheet for complete information.

ADDITIONAL INFORMATION

Packaging	1Lt, 5Lt and 20lt (White only) Tint Bases – Pastel Base 7, Medium Base 8, Deep Base 9 and U/Deep Base 6: 1Lt and 5Lt
Storage Conditions	Store under cool dry conditions away from direct sunlight, heat and extreme cold.
Disclaimers	Colour swatch references are as accurate as modern printing will allow. Among others, the following factors may affect final colour appearance: product sheen and texture, colour and light reflections, application, surface texture and preparation. For best colour and sheen consistency, it is advisable to use containers of the same batch number, or to mix different batches together in a large container, or to finish in a corner before starting a new container.
Tinting Protocol	The tint base containers are only filled to levels which are specific for each tint base to allow the calculated volume of colourants to be added in order to achieve the volume indicated on the container after tinting. Tint bases and colourants are unfinished products which should not be used on their own. Only once the prescribed colourant is added to the specific tint base will the finished product comply with the technical features and related information as set out in this Technical Data Sheet.

DULUX GLOSS ENAMEL

GUARANTEE

Dulux offers a 7-year product guarantee on **Dulux Gloss Enamel** (standard colours and tint bases when tinted with Dulux colourants). **Dulux Gloss Enamel** tinted with non-Dulux colourants is not guaranteed, Dulux has no control over the tinting process or the quality of the colourants used. To register your guarantee, simply call the Dulux Technical Helpline within 30 days of purchase. Simply supply your contact details, the site details, purchase details, batch number and related products used. You will receive a Guarantee Reference Number that you should record and keep in a safe place, together with your purchase slip for future reference. For terms and conditions of the guarantee, please visit www.duluxguarantee.co.za or contact Dulux Technical Helpline on 0860 330 111.

TDS STANDARD DISCLAIMER

The recommendations contained herein are given in good faith and meant to guide the specifier or user in accordance with good painting practices. They are gained from our tests and experiences and are believed to be accurate and reliable. No warranty/guarantee is implied by the recommendations contained herein since the conditions of use; application method, substrate and cleanliness of the substrate are beyond Dulux control.

Important Note; Technology may change with time, necessitating changes to this Technical Data Sheet (TDS).

It is the responsibility of the user to ensure that the latest TDS is being used for reference. Dulux Technical Data Sheets are available on our website www.dulux.co.za or please contact: Dulux On-Line on 0860 330 111. Email ZA.Helpline@akzonobel.com

ICI Dulux (Pty) Ltd is part of AkzoNobel. ICI Dulux (Pty) Ltd Reg No.1946/020769/07